

CODE: AL-156

PRODUCT NAME:

Urethane Alkyd Finishing Coat

DESCRIPTION:

AL-156 is single pack Urethane Alkyd gloss marine enamel providing a tough durable with good abrasion resistance for interior and exterior structures in Semi-Industrial environments above water. AL-156 is not suitable for immersion and should not be used in alkaline conditions. It is not designed for application over epoxies or polyurethanes, and should not be applied over zinc based primers because of dangers specification of the the alkyd resin and consequent adhesion loss.

TECHNICAL DATA:

Binder	Alkyd Modified resin
Pigment	Organic and inorganic pigments
Finish	Gloss
Shade	RAL Colors
Specific gravity	1.1 ± 0.1 Kg/Lit
Volume solid	44 ± 3 %
Flash point	30 °C
Typical dry film thickness	30-50 Microns per one coat
Number of coat	One or two
Substrate	Primed steel , concrete , wood surfaces
Application method	Conventional or air less spray , brush , roller
Thinner / Cleaner	T-100
Weight of added thinner	Max 15%
Theoretical spreading rate (at 30 Mic)	14.7 M ² /Lit
Packing	4 kg or 20 kg
Shelf life	12 Months



Approved b



Drying Time

Temp	Touch dry	Hard dry	Overcoating	
			Min	Max
15°C	7 hours	30 hours	28 hours	-
25°C	4 hours	22 hours	24 hours	-
40°C	2 hours	16 hours	18 hours	-

Note: Drying times are dependent on applied film thickness; all data in this catalogue are reported at recommended DFT.

SURFACE PREPARATION

All surfaces to be coated should be clean, dry and free from contamination. High pressure fresh water wash or fresh water wash, as appropriate, and remove all oil or grease, soluble contaminants, and other detrimental foreign matter in accordance with SSPC-SP1 solvent cleaning.

NEW BUILDING/MAJOR REFURBISHMENT

AL-156 should always be applied over a recommended primer or intermediate coating scheme. The primer surface should be dry and free from all contamination, and AL-156 must be applied within the overcoating intervals specified (consult the relevant product data sheet).

Areas of breakdown, damage etc., should be prepared to the specified standard (e.g. Sa2 ½ (ISO 8501-1:1998), or SSPC-SP-1, Hand/power cleaning) and patch primed prior to the application of AL-156.

AL-156 may be applied directly over aged AL-156 following thorough fresh water washing and degreasing provided the coating to be overcoated is in an intact and tightly adherent condition. Loose or flaking coatings should be removed back to a firm edge and AL-156 or an appropriate primer should be used to repair the area before application of the full coat.

- Surface preparation shall not take place in the following conditions:

- A) At temperature below 5 °C.
- B) When the relative humidity greater than 85%.
- C) When the metal surface temperature is less than 3 °C above the dew point.
- D) Outside day light hours on exterior location.



Application Method:

This material is a one component coating and should always be mixed thoroughly with a power agitator before application.

Application Equipments

Air less Spray	Tip range 0.013-0.016inch Total output pressure at spray tip not less than 141 Bar (2000 psi)
Air Spray	Nozzle Orifice:1.6 -1.8 mm Nozzle Pressure:2-4 Bar (29-58 psi)
Brush	Typically 50 mic can be achieved.
Roller	Typically 50 mic can be achieved.

Flush Equipment with recommended Cleaner before and after use.

ENVIRONMENTAL CONDITIONS:

- For satisfactory cure, air and surface temperature must be above 10 °C.
 - To prevent moisture condensation during application, surface temperature must be at least 3 °C above the dew point.
- Never apply coatings under reverse environmental condition.
Paint shall not be applied when wind speed is in excess of 7 m/s.

Air temperature	10 to 40 °C
Surface temperature	10 to 50 °C
Material temperature	15 to 40 °C
Relative humidity	Max 80 %

Health and Safety:

This product is Flammable. Keep away from heat and open flame .Keep container closed .Use with adequate ventilation. Avoid prolonged and repeated contact with skin. If used in confined areas, observe the following precautions to prevent hazards of fire or explosion or damage to the health:

- 1-Circulate adequate fresh air continuously during application and drying.
- 2-Use fresh air masks and explosion proof equipment.
- 3- Prohibit all flames, sparks, welding and smoking.

Under License C



Approved b

